

 Diamond W



PATCHING



SELF-LEVELERS



PRIMERS



MOISTURE CONTROL



IN STOCK

Ardex Engineered Cements™
SURFACE PREPARATION



PATCHING COMPOUNDS




Feather Finish
(Gray)
FF10G

- True featheredge
- Install floor coverings in as little as 15 minutes
- Exceptional bond strength



Feather Finish XF
(Gray)
FFXF10G

- True featheredge
- Install floor coverings in as little as 15 minutes
- Caster wheel approved



MRF
(Gray)
MRF10

- Engineered to withstand 100% RH
- Unlimited moisture and water
- Install floor coverings in as little as 30 minutes

SELF-LEVELING UNDERLAYMENTS



K 10
K 10 50

- Seeks its own level and provides a durable flat surface
- Install most floor covering after 24 hours



K 13
K 13 50

- Levels and smooths a variety of interior substrates
- Install most floor covering after 16 hours



K 15
K 15 55

- The original and most specified self-leveler in North America
- Install most floor covering after 16 hours



V 1200
V1200 50

- Excellent flow and heal properties
- Install most floor covering after 24 hours



V 1000
V1000 50

- Can be tapered to meet existing elevations
- Install most floor covering after 24 hours

PRIMERS



P 4

P4-1 (1 gal)
P4-3.5 (3.5 gal)

- Pre-mixed, ready to use
- Dries in as little as 30 minutes

CRACK & JOINT REPAIR




ARDIFIX

ARDIFIX (21.2 oz tube)

- Two-part polyurethane with extremely low viscosity for deep penetration
- Ideal for cracks and saw-cuts prior to moisture control, underlayments, and toppings
- Interior or exterior use

MOISTURE CONTROL



MC RAPID

MCRAPID A&B

- One-coat epoxy resin system
- Ready to prime in 4 hours
- For RH up to 100%



VB 100

VB-100-5

- Fast drying, install underlayments in as little as 60 minutes after the second coat
- Reduces moisture vapor emissions in concrete
- For RH up to 100%

ARDEX AMERICAS | Self-Leveling Underlayments

Product Selection Chart		Over concrete	Over ceramic tile and terrazzo	Over non-water-soluble adhesive residue	Well bonded VCT	Epoxy Coating Systems	Metal	Over wood	Over gypsum	Primer, Mechanical Prep	Pumpable	On/Above/Below Grade	Portland Cement-Based	Cement Hybrid	Can be tapered	Mix with water only	Two Component	Maximum thickness neat	With aggregate	Hours to walk on	Hours to install moisture insensitive tile & stone	Hours to install most flooring	Compressive strength (ASTM C109 Modified) at 28 days	Coverage	RH Limit
ARDEX K 10®	High Flow	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	1/2"	5"	2 to 3	6	24	4700 psi (329 kg/cm²)	50 ft² at 1/8" (4.5 m² at 3 mm)	99% RH
	Reg.	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	1 1/2"	12 cm	2 to 3	6	16	5300 psi (371 kg/cm²)	28 ft² at 1/4" (2.6 m² at 6 mm)	99% RH
ARDEX K 13®	High Flow	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	1 1/2"	5"	2 to 3	6	16	5300 psi (371 kg/cm²)	26 ft² at 1/4" (2.4 m² at 6 mm)	99% RH
	Reg.	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	4 cm	12 cm	2 to 3	6	16	5300 psi (371 kg/cm²)	26 ft² at 1/4" (2.4 m² at 6 mm)	99% RH
ARDEX K 15®		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	1 1/2"	5"	2 to 3	6	16	5500 psi (386 kg/cm²)	30 ft² at 1/4" (2.79 m² at 6 mm)	99% RH
ARDEX V 1200™		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	1 1/4"	3 cm	2 to 3	6	24	4500 psi (316 kg/cm²)	25 ft² at 1/4" (2.3 m² at 6 mm)	99% RH
ARDEX V 1000™		●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	●	1 1/4"	3 cm	4 to 5	6	24	4400 psi (309 kg/cm²)	25 ft² at 1/4" (2.3 m² at 6 mm)	99% RH

ARDEX AMERICAS | Non-Structural Patching Compounds

ARDEX		Exterior	Trowel	Pour	Concrete	Wood	Masonry	Terrazzo	Ceramic Tile	Quarry Tile	Adhesive Residues	True Feather Edge	Minimum	Maximum	Walk on	Install Floor Covering	Coverage/ Bag	CHOOSE...	RH Limit
ARDEX FEATHER FINISH®		●	●	●	●	●	●	●	●	●	●	●	Featheredge	1/2 inch 12.7 mm	15 minutes	15 to 20 minutes	300 sq. ft. at a skim coat 27.8 m²	Unrivaled Performance	99% RH
ARDEX FEATHER FINISH® XF™		●	●	●	●	●	●	●	●	●	●	●	Featheredge	1/2 inch 12.7 mm	15 minutes	15 to 20 minutes	300 sq. ft. at a skim coat 27.8 m²	High Performance	95% RH
ARDEX MRF™	interior	●	●	●	●	●	●	●	●	●	●	●	Featheredge	unfilled in well-defined areas	30 minutes	30 minutes	28 sq. ft. at 1/8"	Weatherproof	100% RH
	exterior	●	●	●	●	●	●	●	●	●	●	●	Featheredge	1/4" in well-defined areas	30 minutes	30 minutes	28 sq. ft. at 1/8"	Weatherproof	100% RH